

PRODUCT DATA SHEET

CGFL200 FLOOR GRAPHIC OVERLAMINATE

CGFL200 Floor graphic overlaminate is suitable for short term floor graphics, or general signage applications where a matt sand finish or abrasion resistance is required. CGFL200 has passed CSIRO slip resistance test to an R10 level, this documentation is available upon request.

APPLICATIONS

- Internal Floor Graphics
- Point of sale
- Table Tops
- Anti-Slip

TECNICAL DATA

Test Term	Units	Test Method	Average Value
Thickness PVC	Micron	GB/T6672-2001	200 ± 10
Weight of Liner	g/m ²	GB4669-1995	120 ± 10
Weight of Finished Product	g/m ²	GB4669-1995	360 ± 20
Initial Adhesion	N/25mm	FTM 9	≥5
24h, 180° Peel	N/25mm	FTM 1	≥8
Dimensional Stability MD	mm	FTM 14	≥1.8
Dimensional Stability CD	mm	FTM 14	≥1.5
Tensile Strength MD	N/25mm	GB/T1040.1-2006	≥60
Tensile Strength CD	N/25mm	GB/T1040.1-2006	≥70
Construction Temperature	°C		20±10°C
Applicable Temperature	°C		20 ~ +70

INSTALLATION

We suggest you allow 24-48 hours for the print to dry prior to lamination. Always clean application free of dust, dirt, debris and other contaminants. We recommend cleaning the installation surface with isopropyl alcohol prior to application.

All information stated within this Product Data Sheet is intended for reference purposes only. The information does not suggest or constitute a verbal or written warranty. The end user shall be responsible for the testing and suitability of their application prior to final use.