

### PRODUCT DESCRIPTION

ICON® PL-3150 is a 2.75mil flexible clear polymeric vinyl overlaminating film, backed with a solvent-based permanent adhesive system. ICON® PL-3150 provides industry leading gloss, clarity, and conformability. An exceptional choice for short to medium-term indoor/outdoor signage, POP/tradeshow graphics, decals, race cars, nameplates, fleet graphics, and more! PL-3150 has obtained a Class A fire rating in ASTM E84-17 testing and Meets the highest life safety requirements for indoor/oudoor commercial graphics.

# RECOMMENDED ENDUSES

Substance Incorporated ICON® PL-3150 exhibits the following product features and advantages:

- Superior protection of digitally printed graphics and signs with exceptional clarity.
- Protection of permanent indoor/outdoor signage with a medium-term lifespan.
- Permanent graphic installations on flat to mildy curved surfaces.
- Unmatched gloss, conformability, and clarity with a UV extension factor of 3 years.
- Phthalate-Free Film Structure and ASTM E84-17 Class A rating conform to the highest heath and safety standards.

#### PERFORMANCE CHARACTERISTICS

MATERIAL  COLOR  Clear  TENSILE STRENGTH  12.5 Pounds/Inch  ADHESIVE  Clear Solvent-Based Permanent Pressure Sensitive Acrylic  ADHESIVE THICKNESS  1.1mil  PEEL ADHESION  4.5 Pounds/Inch from Stainless Steel  LINER  90LB PE Coated Layflat Paper  LINER RELEASE  30 Grams/Inch  DIMENSIONAL STABILITY  0.020 Inch (Machine Direction)  APPLICATION TEMP.  50°F to 90°F recommended, test prior to specific application  TEMPERATURE RANGE  -40°F to 190°F
TENSILE STRENGTH  ADHESIVE  Clear Solvent-Based Permanent Pressure Sensitive Acrylic  ADHESIVE THICKNESS  1.1mil  PEEL ADHESION  4.5 Pounds/Inch from Stainless Steel  LINER  90LB PE Coated Layflat Paper  LINER RELEASE  30 Grams/Inch  DIMENSIONAL STABILITY  0.020 Inch (Machine Direction)  APPLICATION TEMP.  50°F to 90°F recommended, test prior to specific application  TEMPERATURE RANGE  -40°F to 190°F
ADHESIVE Clear Solvent-Based Permanent Pressure Sensitive Acrylic ADHESIVE THICKNESS 1.1mil PEEL ADHESION 4.5 Pounds/Inch from Stainless Steel LINER 90LB PE Coated Layflat Paper LINER RELEASE 30 Grams/Inch DIMENSIONAL STABILITY 0.020 Inch (Machine Direction) APPLICATION TEMP. 50°F to 90°F recommended, test prior to specific application TEMPERATURE RANGE -40°F to 190°F
ADHESIVE THICKNESS  1.1mil  PEEL ADHESION  4.5 Pounds/Inch from Stainless Steel  LINER  90LB PE Coated Layflat Paper  LINER RELEASE  30 Grams/Inch  DIMENSIONAL STABILITY  0.020 Inch (Machine Direction)  APPLICATION TEMP.  50°F to 90°F recommended, test prior to specific application  TEMPERATURE RANGE  -40°F to 190°F
PEEL ADHESION  4.5 Pounds/Inch from Stainless Steel  LINER  90LB PE Coated Layflat Paper  LINER RELEASE  30 Grams/Inch  DIMENSIONAL STABILITY  0.020 Inch (Machine Direction)  APPLICATION TEMP.  50°F to 90°F recommended, test prior to specific application  TEMPERATURE RANGE  -40°F to 190°F
LINER 90LB PE Coated Layflat Paper  LINER RELEASE 30 Grams/Inch  DIMENSIONAL STABILITY 0.020 Inch (Machine Direction)  APPLICATION TEMP. 50°F to 90°F recommended, test prior to specific application  TEMPERATURE RANGE -40°F to 190°F
LINER RELEASE 30 Grams/Inch  DIMENSIONAL STABILITY 0.020 Inch (Machine Direction)  APPLICATION TEMP. 50°F to 90°F recommended, test prior to specific application  TEMPERATURE RANGE -40°F to 190°F
DIMENSIONAL STABILITY  0.020 Inch (Machine Direction)  APPLICATION TEMP.  50°F to 90°F recommended, test prior to specific application  TEMPERATURE RANGE  -40°F to 190°F
APPLICATION TEMP. 50°F to 90°F recommended, test prior to specific application TEMPERATURE RANGE -40°F to 190°F
TEMPERATURE RANGE -40°F to 190°F
10.100
SHELF LIFE 2 years when stored at 70°F and 50% relative humidity
PRINT COMPATIBILITY Solvent, Eco-Solvent, Latex, UV, and Thermal Transfer Inks
GRAPHIC LIFE Outdoor durability up to 5 years, permanent
CHEMICAL RESISTANCE Resists mild acids, mild akalis, solvents, and salts
Excellent resistance to water, including immersion

#### INSTALLATION RECOMMENDATIONS

- Before applying an overlaminate, please allow 24-48 hours for solvent ink systems to dry.
- Application surface should be free of dust, dirt, debris, grease, and other contaminants.
- It is highly recommended to clean the installation surface with isopropyl alcohol prior to application.
- Dry installation is recommended. If a wet installation is desired, please test application fluid prior to use in a production environment.



## NOTICE

Substance Incorporated products are precision manufactured in the United States to the highest exacting standards, and guaranteed to be free from manufacturing defects. All descriptive information presented within this Product Data Sheet is intended for reference purpose only. This information does not suggest or constitute a verbal or written warranty of any kind. The end user shall be responsible for independently testing the suitability of this product for their aplication, prior to final use. Substance Incorporated shall not be held liable for damages, injuries, loss, or expenses that result from the use of our products. Our unique Phthalate-Free Film Structure meets the health and safety requirements set forth by CPSIA, REACH, ROHS, and California Proposition 65.

